

Europäisches Patentamt European Patent Office Office européen des brevets



(11) EP 1 206 959 A1

(12)

EUROPEAN PATENT APPLICATION published in accordance with Art. 158(3) EPC

- (43) Date of publication: 22.05.2002 Bulletin 2002/21
- (21) Application number: 99944646.1
- (22) Date of filing: 27.08.1999

- (51) Int CI.7: **B01D 53/22**, B01D 67/00, B01D 71/68, B01D 69/08
- (86) International application number: PCT/ES99/00279
- (87) International publication number: WO 01/07148 (01.02.2001 Gazette 2001/05)
- (84) Designated Contracting States:

 AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU

 MC NL PT SE

 Designated Extension States:

 AL LT LV MK RO Si
- (30) Priority: 22.07.1999 ES 9901652
- (71) Applicant: David Systems Technology S.L. 28006 Madrid (ES)
- (72) Inventor: BLACH VIZOSO, Ricardo E-48950 Asua-Erandio (ES)
- (74) Representative: Carpintero Lopez, Francisco HERRERO & ASOCIADOS, S.L. Alcalá, 35 28014 Madrid (ES)

(54) POLYMER MEMBRANE FOR THE SEPARATION OF GAS MIXTURE

(57) This membrane comprises asymmetric hollow fibre of polyethersulphide for the purpose of pervaporation, treated with mixtures of liquids (C2H50H+X) in which X=toluene, acetone, dimethylformamide with a

content of between 7 - 12% by volume of the mixture, subsequently treated with a solution at 2.5% by volume of urethanosiloxane in isopropylic alcohol.

Description

20

25

45

OBJECT OF THE INVENTION

[0001] The invention is destined to the technology of membranes for separating mixtures of gases and can be applied to a chemical product, oil refineries, the natural gas industry, as well as other branches of the petrochemical industry, and it can be used for the separation of technological gaseous mixtures, including hydrogen and/or components of natural gas with a broad content of hydrogen sulphide and heavy hydrocarbons.

10 BACKGROUND OF THE INVENTION

[0002] Currently, progress in the technologies of chemical products is connected to the new technologies for saving energy. One of these prospective procedures is the separation of mixtures of gases using membranes.

[0003] The procedures using membranes are attractive for technicians because of their low behavioural waste in the field, the simplicity of the equipment and servicing, and the absence of heat-exchange equipment.

[0004] From the mid-80s onwards, separation using membranes has displaced traditional methods for dividing gases, such as the cryogenic method for division and absorption function under pressure. At the moment, the membrane technology has become the most widespread in the following sectors of the industry:

- · separation of hydrogen in chemical procedures of oil and refining of oil;
- elimination of carbon dioxide from natural gas;
- · separation of air to yield highly enriched nitrogen, and enriched before the 40% flow of oxygen in whole air.

[0005] One of the most important applications of membranes of polymers is the separation and refining of hydrogen from combustible gases produced by oil refineries. This is explained by the main very high cost of producing hydrogen in installations with just one aim, and the possibility of using any other source to obtain hydrogen is very interesting for specialists.

[0006] The main sources of residual gases that contain hydrogen from the chemistry of oil are:

- purging of synthesis gas from ammonia;
 - purging the gases in the production of methanol, styrene and others;
 - the residual gas from cracking by vapour;
 - the residual gas from the hydrodealkylation of toluene.
- 35 [0007] The sources of residual gases in the processes of oil refining are:
 - residual gas from catalytic reforming;
 - residual gas from catalytic cracking;
 - exhaust gas from hydro-desulphuration;
- exhaust gas from hydrocracking.

[0008] However, it is necessary to observe that the use of polymer membranes was used normally by the media with heavy hydrocarbon contents less than 3-4% by volume, when the contents were greater, a reversible plasticising effect was observed with loss of the selective characteristics, but without mechanical destruction. Investigations of the inventors have demonstrated that when the concentrations of heavy hydrocarbons are reduced to below 2-3% by volume, selective characteristic is gradually restored (but not to more than 80% of the initial value).

[0009] The majority have chosen the method of membranes to eliminate carbon dioxide from natural gas. The membrane technology allows, in a similar procedure of a single stage, a reduction in the concentration of CO₂ from 5-7% by volume to 1.0-1.5% by volume. They were carried out first with a membrane based on cellulose acetate from "Separex Corporation" [Schell W. J. and co-workers, J. Chem. Eng. Progress. 1982, v. 78, no. 10, pp. 33-37], and also polysulphone from the company "Monsanto" [Monsanto Company], Prism Separators by Monsanto. For a variety of different sources of natural gas (Russia, Canada, SAR), these membranes need a significant modernisation in the sense that in the natural gas from these countries there is a high content of up to 40% of hydrogen sulphide. The investigations of the inventors under laboratory and industrial conditions have shown that the polymeric membrane of cellulose acetate, in the media with hydrogen sulphide contents of 5-7% by volume, rapidly becomes plasticised and loses the basic characteristics.

OBJECT OF THE INVENTION

10

15

35

45

50

55

[0010] The main characteristics that define the capacity for commercialising the membrane are as follows:

- Selectivity of the membrane for the separation of the main components. For an efficient commercial use for separation of natural gas and/or gas that contains hydrogen, a membrane should have a selectivity for the H₂-CH₄ pair of not less than 50, and for the CO₂-CH₁ pair of not less than 30. Lower values of selectivity lead to the use of multi-stage schemes for the object component, which require additional compression, thus increasing the energy demands and leading to useless losses of gas.
 - Specific productivity. The specific productivity of a membrane is defined by its type and structure, as well as by the design of the membrane separator (as equipment). In as far as the procedures for membrane separation are based on the differences in solubility of the gases in the polymer and the diffusion of gases through it, the capital expenditure for the installation of the membrane is defined by the thickness of the selective barrier formed by the membrane. On the other hand, the membrane should be able to withstand a significant pressure on its walls (below 5-7 Mpa). Thus, the most widely used types of polymer membrane that are employed commercially are of asymmetric type and of compound material.
- Geometry of the membrane. This parameter is defined in the stage of creating the membrane separator. Three main types of design are known for the membrane elements (bundle): a) flat-sheet fibre, b) spiral form and c) hollow. For the first two, the flat sheet membrane is used in the form of laminas stuck together or with revolutions in the form of a spiral, as required. The third type of design comprises fixing a membrane fibre in a sheaf, later fixed in a membrane device. The fibre-type is the one with best prospects.
- 25 Chemical stability to the components of the mixture to be separated.

[0011] Bearing in mind the requirements described above, the polymers with greatest prospects for creating membranes are polysulphone, polyethersulphone, polymers that contain fluorine, polyamidoimide.

[0012] The isotopic membrane of hollow fibre, produced from poly-4-methylpentene-1, is well known (commercial name in Russia is "Graviton"), which is used in Russia in membrane installations for separating gaseous mixtures, including components of natural gas [Kostrov Yu. A. and co-workers, Scientific Journal "Chemical Fibers", 1986, No. 6, pp. 49-51].

[0013] The disadvantages of the aforementioned membrane can be attributed to the following characteristics:

- isotropic structures, and as a result, with low specific productivity;
 - low selectivity:
 - low selective properties after working with mixtures in which the concentration of heavy hydrocarbons (C₁ and heavy) is greater than 8% by volume.
- [0014] The hollow fibre membrane made from composite material from polypropylene is well known, with a selective layer made from polyethersulphone [EP MC14 B 01D 13/04, B 01D 53/22, No. 0 174 918, 1985].

[0015] The disadvantages of the membranes made from composite materials can be attributed to the following characteristics:

- technological complexity involved in applying a homogeneous selective layer to the polypropylene support;
 - possibility of the distraction of the selective layer, including its extraction.

[0016] The immediate technical solution to this problem is an asymmetric hollow fibre of polyethersulphone, produced from a hollow fibre of initial gas separation with an initial selectivity for the H₂/CH₄ pair < 5 by means of modification in a solution of HBr/n-C₅ 0.02 M with a posterior treatment under vacuum of up to 24 hours [US patent, NC1 55/16, No. 4 472 175, 1984].

[0017] The disadvantages of this solution that can be mentioned are as follows:

- loss of a selectivity reached after modification during a period of operation (the selectivity of the hydrogen/methane pair is constantly reduced: after 1 day of operation the selectivity is 147, after 6 days - 35 and so on);
 - · short usage times for modification of the liquid solution;
 - need to keep the membrane treated under vacuum in order to achieve the selective properties required up to 24 hours.

DESCRIPTION OF THE INVENTION

[0018] The technical results of the technical solution, created by the authors of the present invention for the production of an asymmetric hollow fibre membrane from polyethersulphone are as follows:

- good selective properties which remain stable over the period of usage;
- selectivity required for the procedures of separation of hydrogen and/or components of natural gas with a high content of H₂S (up to 40% by volume) and heavy hydrocarbons (up to 15% by volume).

10 [0019] The technical result is achieved because the polymer membrane for separation of gas for dividing the components of natural gas has a special construction:

- firstly the asymmetric hollow fibre membrane made from polyethersulphone is treated for the pervaporation with mixtures of liquids such as C₂H₅OH + X, in which X = toluene, acetone, dimethylformamide, with a concentration of X = 7-12% by volume;
- · then the membrane is treated with a solution of 2.5% by volume of urethanosiloxane in isoamylic alcohol;
- it is then treated with a gaseous mixture of F₂- HF inert gas; the content of the inert gas varies from 0 to 90%, and the concentration of HF in the current of F₂ is equal to 4-6% by volume.

[0020] The polymer membrane is produced by the following procedure: an initial hollow fibre of polyethersulphone is treated with the mixtures of organic liquids (C_2H_5OH -toluene, C_2H_5OH -acetone or C_2H_5OH -dimethylforamidae with a content of organic solvents of C_2H_5OH equal to 7-12% by volume in a period of 60-90 minutes with a near vacuum pump at a temperature of T = 298 K for 15 minutes.

[0021] The dry hollow fibre is treated with solution at 2.5% by volume of urethanosiloxane (for example, siloethane) in isopropanol.

[0022] Then the hollow fibres are modified in gaseous phase with a mixture of F_2 :HF:N₂ (He).

[0023] The content of inert components varies from 0 to 90% by volume, the content of \overline{HF} in F_2 is 4-6% by volume. In table No. 1 the real separation factors are shown form the pairs H_2/CH_4 and CO_2/CH_4 for the hollow fibre membrane, produced in the aforementioned procedure.

Table I

	Characteristics of separation of the polyr	ner membrane of hollow fibre	produced	
No.	Treatment of organic solutions	Modification in gas phase	Separation factor	
			H ₂ /CH ₄	CO ₂ /CH ₄
1		with no modification	1.8	7
2	solution 8% of toluene in C ₂ H ₅ OH	with no modification	71	41
3	solution 8% of toluene in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =20: 80% vol	84	47
4	solution 8% of toluene in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =40: 60% vol	79	-
5	solution 10% of toluene in C ₂ H ₅ OH	with no modification	69	35
6	solution 10% of toluene in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =20: 80% vol	79	41
7	solution 12% of toluene in C ₂ H ₅ OH	with no modification	67	35
8	solution 12% of toluene in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =20: 80% vol	79	40
9	solution 12% of toluene in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =40: 60% vol	73	37
10	solution 11% of acetone in C ₂ H ₅ OH	with no modification	92	45
11	solution 11% of acetone in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =20: 80% vol	97	53
12	solution 11% of acetone in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =10: 90% vol	103	56
13	solution 11% of acetone in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =40: 60% vol	96	-
14	solution 11% of acetone in C ₂ H ₅ OH	F ₂ +HF=100% vol	94	50
15	solution 7% of acetone in C ₂ H ₅ OH	With no modification	84	43

15

20

25

35

40

45

50

55

Table I (continued)

	Characteristics of separation of the polymer membrane of hollow fibre produced				
No.	Treatment of organic solutions	Modification in gas phase	Separation factor		
			H ₂ /CH ₄	CO ₂ /CH ₄	
16	solution 7% of acetone in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =20 : 80% vol	93	47	
17	solution 7% of acetone in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =10: 90% vol	97	50	
18	solution 7% of acetone in C ₂ H ₅ OH	F ₂ +HF=100% vol	88	44	
19	solution 9% of dimethylformamide in C_2H_5OH	Not treated	58	34	
20	solution 9% of dimethylformamide in C_2H_5OH	(F ₂ +HF) :N ₂ =20: 80% vol	71	44	
21	solution 9% of dimethylforamide in C ₂ H ₅ OH	(F ₂ +HF) :N ₂ =10: 90% vol	67	41	

[0024] The results obtained show that the samples of the membrane treated with mixtures of organic liquids which are then treated with urethanosiloxane and/or modifiers with gaseous mixtures that contain fluorine, allow selective characteristics to be obtained. These are better than the selective properties of the initial polyethersulphone.

[0025] The gas phase modification can be carried out over a broad range of concentrations of fluorine and treatment times. The results attained are stable for a long time.

[0026] The samples of membrane, treated with fluorine, conserve the selective properties in a medium with a high concentration of H_2S and heavy hydrocarbons. The assumed properties of the membrane produced depend on the properties of separation of the initial membrane, the content of the mixture of liquids and the conditions of modification (concentration of fluorine, pressure of the modified mixture of gas, treatment time).

EXAMPLES FOR A PREFERRED EMBODIMENT OF THE INVENTION

Example 1

5

10

15

20

25

30

35

45

55

[0027] An asymmetric hollow fibre of polyethersulphone is treated by pervaporation in an 8% solution (by volume) of toluene in C_2H_5OH for 65 minutes, then dried under vacuum for 15 minutes and then treated in 2.5% (by volume) solution of urethanosiloxane with isopropanol for 60 seconds. The hollow fibre is dried in air for 12 hours in order to attain the stable separation factor for the pair $H_2/CH_4 = 71$, $CO_2/CH_4 = 41$.

Example 2

[0028] An asymmetric hollow fibre of polyethersulphone is treated by pervaporation in an 11% solution (by volume) of acetone in C_2H_5OH for 75 minutes, then dried under vacuum for 15 minutes and then treated at 2.5% (by volume) of urethanosiloxane with isopropanol for 60 seconds. The hollow fibre is dried in air for 12 hours. After drying, the hollow fibre membrane is modified with a gaseous mixture (F_2+HF): $N_2=10:90$ (by volume) for 60 minutes. This results in an additional increase in the separation factor from 92 to 103 for the H_2/CH_4 pair, and from 45 to 56 for the CO_2/CH_4 pair. The membrane produced in this procedure maintained its properties when used in the medium $H_2S:CH_4=40:60$ pressure of 0.3 MPa) for 240 hours.

Example 3

[0029] An asymmetric hollow fibre of polyethersulphone is treated by pervaporation in a 9% solution (by volume) of dimethylformamide in C_2H_5OH for 85 minutes, then dried under vacuum for 15 minutes and then treated in 2.5% (by volume) solution of urethanosiloxane with isopropanol for 60 seconds. The hollow fibre is dried in air for 12 hours. After drying, the hollow fibre membrane is modified with a gaseous mixture (F_2+HF): $N_2=20$:80 (by volume) for 120 minutes. This results in an additional increase in the separation factor from 58 to 71 for the H_2/CH_4 pair, and from 34 to 44 for the CO_2/CH_4 pair. The membrane produced in this procedure maintained its properties when used in the medium $CH_4=(C_3H_8+C_4H_{10}+C_5H_{12})=85$:15 (pressure of 0.1 MPa) for 240 hours.

Example 4

[0030] An asymmetric hollow fibre of polyethersulphone is treated by pervaporation in a 12% solution (by volume)

EP 1 206 959 A1

of toluene in C_2H_5OH for 60 minutes, then dried under vacuum for 15 minutes and then treated in 2.5% (by volume) solution of urethanosiloxane with isopropanol for 60 seconds. The hollow fibre is dried in air for 12 hours. After drying, the hollow fibre membrane is modified with a gaseous mixture (F_2+HF): $N_2=20:80$ (by volume) for 45 minutes. This results in an additional increase in the factor of separation from 67 to 79 for the H_2/CH_4 pair and from 35 to 40 for the CO_2/CH_4 pair. The membrane produced in this procedure kept its properties when used in the medium $H_2S:CH_4=40:60$ pressure 0.3 MPa) for 240 hours.

Example 5

[0031] An asymmetric hollow fibre of polyethersulphone is treated by pervaporation in a 7% solution (by volume) of acetone in C₂H₅OH for 90 minutes, then dried under vacuum for 15 minutes and then treated in 2.5% (by volume) solution of urethanosiloxane with isopropanol for 60 seconds. The hollow fibre is dried in air for 12 hours. After drying, the hollow fibre membrane is modified with a gaseous mixture (F₂+HF):N₂ = 10:90 (by volume) for 60 minutes. This results in an additional increase in the separation factor from 84 to 97 for the H₂/CH₄ pair and from 43 to 50 for the CO₂/CH₄ pair. The membrane produced in this procedure maintained its properties when used in the medium CH₄: (C₃H₈ + C₄H₁₀ + C₅H₁₂) = 85:15 (pressure 0.1 MPa) for 240 hours.

Use of the invention allows:

20 [0032]

25

30

45

50

55

- the process of separation to be performed for gaseous mixtures that contain H₂ or components of natural gas, with greater efficiency than the membranes produced up until now;
- * separation of mixtures with high content of H₂S (up to 40% by volume) and heavy hydrocarbons (up to 15% by volume):
- * changing the conditions of modification and/or treatment to produce membranes with different properties required over the base of a single type of initial membrane hollow fibre membrane of polyethersulphone for pervaporation;
- * increasing the sphere of use for the pervaporation membrane;
- * using a modification of fluorine in gas phase in all the stages of the creation of the membrane separator: as a membrane, as a bundle (element of the membrane) or separator of prepared membrane.

Claims

- 35 1. A polymer membrane for the separation of components of natural gas, that comprises an asymmetric hollow fibre of polyethersulphone for the purposes of pervaporation, treated with mixtures of liquids (C2H5OH + X), in which X = toluene, acetone, dimethylformamide, with a content of X=7-12% (by volume) in the mixture, subsequently treated with a solution at 2.5% (by volume) of urethanosiloxane in isopropylic alcohol.
- 40 2. A polymer membrane, according to claim 1, characterised in that a hollow fibre membrane of polyethersulphone is used, modified with a gaseous mixture [(F₂ HF) : inert gas] with content of (F₂ HF) in the range 0-90% (by volume), and concentration of HF in fluorine of 4-6% (by volume).

6

e . . . 4

INTERNATIONAL SEARCH REPORT

International application No. PCT/ES 00/00279

		101/20		
A. CLASSI	FICATION OF SUBJECT MATTER			
	53/22; 67/00; 71/68; 69/08			
According to	International Patent Classification (IPC) or to both na SEARCHED	tional classification and IPC		
PC 6 B01E				
Documentati	on searched other than minimum documentation to the	extent that such documents are incl	luded in the fields searched	
	ata base consulted during the international search (nam DC, CIBEPAT	e of data base and, where practical,	search terms used	
C. DOCUM	ENTS CONSIDERED TO BE RELEVANT			
Category*	Citation of document, with indication, where a	opropriate, of the relevant passag	ges Relevant to claim No.	
х	US-4828585 A (CHERRY C.CHIAO) 9 May 1	989 (09.05.89); Example 2	1-2	
Α	US-5085676 A (OKAN M. EKINER et al.) 4 F	ebruary 1992 (04.02.92)		
Α	US-4746333 A (KLAUS V. PEINEMMAN) 24	May 1988 (24.05.88)		
	·			
Furth	er documents are listed in the continuation of box C.			
Special categ	ories of cited documents:	"T" later document published after the	he international filing date or with the application but cited to	
	it defining the general state of the art which is not ed to be of particular relevance	understand the principle or theo	ry underlying the invention	
E" earlier do date	cument but published on or after the international filing	"X" document of particular relevance considered movel or cannot be constep when the document is taken	onsidered to involve an inventive	
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means		"Y" document of particular relevance; the claimed invention cannot considered to involve an inventive step when the document is combined with one or more other such documents, such		
		combination being obvious to a person skilled in the art "&" document member of the same patent family		
P" documen	at published prior to the international filing date but later priority date claimed	a comment mention of the same p	Sales turniy	
ate of the ac	ctual completion of the international search er 1999 (22.12.99)	Date of mailing of the international 28 December 1999 (28.12.99)	al search report	
Name and mailing address of the ISA/ S.P.T.O		Authorized officer		
		Telephone No.		
		L		

Form PCT/ISA/210 (second sheet) (July 1998)

e 4 - 5

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/ ES 00/00279

Patent document Cited in search report	Publication date	Patent family member(s)	Publication date
US - 4828585	09.05.1989	NONE	
US - 5085676	04.02.1992	EP-0489418 A CA-2056921 A JP-4277019 A	10.06.1992 05.06.1992 02.10.1992
US - 7476333	24.05.1988	DE-3525235 C JP-62014916 A EP-0214360 A DK-8603304 A	27.11.1986 23.01.1987 18.03.1987 16.01.1987

8